

Stucco Italiano



STUCCO AQUAGUARD WALL PLASTER

DESCRIPTION

STUCCO AQUAGUARD WALL PLASTER creates a luxurious, natural, smooth finish with a mottled look, suitable for interior as well as exterior walls. Applied with a steel trowel onto concrete, cement plaster, fairface brickwork and many other types of wall surfaces, it creates a mottled finish that matures over time.

PURPOSE

STUCCO AQUAGUARD WALL PLASTER provides a tough, waterproofing durable cement-based plaster for interior as well as exterior walls, available in a range of colours.

APPLICATION

Necessities

1 bag of 20kg STUCCO AQUAGUARD WALL PLASTER; 4.5lt STUCCO AQUAGUARD LIQUID; 40lt mixing bowl; measuring jug; gloves; steel trowel; trowel board; masking tape; drop sheets.

Preparation

Surface must be clean and free from any dust, saline deposits, greasiness or any materials that can prevent binding.

Saline deposits and greasiness can be washed off with washing soda.

The ideal surface for application of STUCCO AQUAGUARD WALL PLASTER is a wood floated cement plastered wall.

When a wall, that has to be covered with STUCCO WALL PLASTER, has got different finishes on the same wall or in the same room e.g. partly covered with an oil based paint, partly cement plaster etc., it is recommended that the entire wall is painted and thoroughly sealed with STUCCO EXTERIOR SEALER (2 coats if required) to avoid colour differences. Apply STUCCO PRE-SCREED onto dried sealer and then **STUCCO AQUAGUARD WALL PLASTER** .

Never apply Stucco to Cretestone covered walls.

In case of a smooth, glossy, textured paint such as oil based paint, sand the surface and remove dust to obtain a sound bonding surface.

In case of a wall being very uneven, it is recommended to first apply a pre-screed layer of STUCCO WALL SKIM to smooth out any unevenness, let it cure and then apply one layer of STUCCO AQUAGUARD WALL PLASTER.

Mixing Instructions

Pour the 4.5lt STUCCO AQUAGUARD LIQUID into a 40lt mixing bowl.

Gradually add the STUCCO AQUAGUARD WALL PLASTER powder, while continuously mixing with hands (covered with gloves), to prevent lumps from being formed, until the full amount of 20kg STUCCO AQUAGUARD WALL PLASTER powder is thoroughly mixed.

The product will have a soft paste-like consistency.

Application

Cover windows, doors and light fittings with masking tape and paper and put drop sheets on floor.

Stucco Italiano



Using a steel trowel, apply and spread the mixed plaster to a smooth finish of 2 – 3mm thick. Wait until the plastered has cured to such extent that it is “dry” but still pliable. Go back onto the wall and finish to a smooth finish with steel trowel to eliminate trowel marks and create a mottled appearance. This cured stage is determined by environmental temperature and humidity.

Work from one corner/edge/joint, always keeping a wet edge to prevent unsightly dry joints.

DO NOT add extra water in any way during application

SEALERS

Leave the walls to dry for about 1 day before applying STUCCO EXTERIOR SEALER or STUCCO INTERIOR WALL SEALER.

Interior walls: Apply a single layer of STUCCO INTERIOR WALL SEALER with a paintbrush or roller.

In a bathroom, apply in the shower one coat of STUCCO COLOUR FASTENER and allow to dry overnight. Apply two coats of STUCCO FLOOR SEALER (Gloss/ Low Sheen/ Matt) 18 hours apart.

Exterior walls: Apply a single layer of STUCCO COLOUR FASTENER and then apply a single layer of STUCCO EXTERIOR SEALER with a spray-can or a roller.

Allow sealers to cure for 48 hours.
(See sealer data sheets)

TECHNICAL DATA

Type:	Cement based
Drying time:	12 hours @ 20°C
Shelf life:	6 months
Coverage:	6½ - 9½ m ² per 20KG bag (one coat, 2-3mm)
Packaging:	20kg powder in paper bags 4.5lt liquid in plastic bottles
Storage:	Store in a cool dry place

WARNING

Do not ingest. Keep away from children and pets. Do not empty into drains.

PRECAUTIONS

Wear rubber gloves. In the event of contact with eyes or skin, rinse thoroughly with cold water. If irritation or discomfort occurs, seek medical advice.

MANUFACTURED BY

Stucco Italiano
25 Industria Rd
Brackenfell
Tel: 021- 982 0006
Fax: 021-982 3796
E-mail: info@stuccoitaliano.co.za
www.stuccoitaliano.co.za